

LAW OFFICES
SUGHRUE, MION, ZINN, MACPEAK & SEAS, PLLC

2100 PENNSYLVANIA AVENUE, N.W.
WASHINGTON, DC 20037-3213
TELEPHONE (202) 293-7060
FACSIMILE (202) 293-7860

July 27, 1999

BOX PATENT APPLICATION
Assistant Commissioner for Patents
Washington, D.C. 20231

Re: Hisashi WATANABE, Yoshio UCHIDA
ALUMINA SINTERED BODY AND PROCESS
FOR PRODUCING THE SAME
Our Ref. Q55086

Dear Sir:

Attached hereto is the application identified above including 50 sheets of the specification, claims, and 2 sheets of Tables. The executed Declaration and Power of Attorney and Assignment will be submitted at a later date. Also enclosed is a Preliminary Amendment.

The Government filing fee, after entry of the Preliminary Amendment is calculated as follows:

Total claims	<u>12</u>	-	20	=		x	\$18.00	=	<u>\$0.00</u>
Independent claims	<u>1</u>	-	3	=		x	\$78.00	=	<u>\$0.00</u>
Base Fee									<u>\$760.00</u>


TOTAL FILING FEE

\$760.00

A check for the statutory filing fee of \$760.00 is attached. You are also directed and authorized to charge or credit any difference or overpayment to Deposit Account No. 19-4880. The Commissioner is hereby authorized to charge any fees under 37 C.F.R. §§ 1.16 and 1.17 and any petitions for extension of time under 37 C.F.R. § 1.136 which may be required during the entire pendency of the application to Deposit Account No. 19-4880. A duplicate copy of this transmittal letter is attached.

Priority is claimed from July 29, 1998, and December 15, 1998, based on Japanese Application Nos. 10-213947, and 10-356002 respectively. The priority documents will be filed at a later date.

Respectfully submitted,
SUGHRUE, MION, ZINN,
MACPEAK & SEAS, PLLC
Attorneys for Applicant

By: 
J. Frank Osha
Registration No. 24, 625

PATENT APPLICATION

IN THE UNITED STATES PATENT AND TRADEMARK OFFICE

In re application of

Hisashi WATANABE, et al.

Appln. No.:

Group Art Unit:

Filed: July 27, 1999

Examiner:

For: ALUMINA SINTERED BODY AND PROCESS FOR PRODUCING THE SAME

PRELIMINARY AMENDMENT

Assistant Commissioner for Patents
Washington, D.C. 20231

Sir:

Prior to examination, kindly amend the above-identified application as follows:

IN THE SPECIFICATION:

Page 20, before line 1, please insert --The results are shown in Table 1.--

REMARKS

The specification has been amended to include a description of Table 1.

Respectfully submitted,



J. Frank Osha
Registration No. 24, 625

SUGHRUE, MION, ZINN,
MACPEAK & SEAS, PLLC
2100 Pennsylvania Avenue, N.W.
Washington, D.C. 20037-3213
Telephone: (202) 293-7060
Facsimile: (202) 293-7860

Date: July 27, 1999

TITLE OF THE INVENTION

Alumina Sintered Body and Process for Producing the Same

BACKGROUND OF THE INVENTION

Field of the Invention

30
31
32
33
34
35
36
37
38
39
40
41
42
43
44
45
46
47
48
49
50
51
52
53
54
55
56
57
58
59
60
61
62
63
64
65
66
67
68
69
70
71
72
73
74
75
76
77
78
79
80
81
82
83
84
85
86
87
88
89
90
91
92
93
94
95
96
97
98
99
100
101
102
103
104
105
106
107
108
109
110
111
112
113
114
115
116
117
118
119
120
121
122
123
124
125
126
127
128
129
130
131
132
133
134
135
136
137
138
139
140
141
142
143
144
145
146
147
148
149
150
151
152
153
154
155
156
157
158
159
160
161
162
163
164
165
166
167
168
169
170
171
172
173
174
175
176
177
178
179
180
181
182
183
184
185
186
187
188
189
190
191
192
193
194
195
196
197
198
199
200
201
202
203
204
205
206
207
208
209
210
211
212
213
214
215
216
217
218
219
220
221
222
223
224
225
226
227
228
229
230
231
232
233
234
235
236
237
238
239
240
241
242
243
244
245
246
247
248
249
250
251
252
253
254
255
256
257
258
259
260
261
262
263
264
265
266
267
268
269
270
271
272
273
274
275
276
277
278
279
280
281
282
283
284
285
286
287
288
289
290
291
292
293
294
295
296
297
298
299
300
301
302
303
304
305
306
307
308
309
310
311
312
313
314
315
316
317
318
319
320
321
322
323
324
325
326
327
328
329
330
331
332
333
334
335
336
337
338
339
340
341
342
343
344
345
346
347
348
349
350
351
352
353
354
355
356
357
358
359
360
361
362
363
364
365
366
367
368
369
370
371
372
373
374
375
376
377
378
379
380
381
382
383
384
385
386
387
388
389
390
391
392
393
394
395
396
397
398
399
400
401
402
403
404
405
406
407
408
409
410
411
412
413
414
415
416
417
418
419
420
421
422
423
424
425
426
427
428
429
430
431
432
433
434
435
436
437
438
439
440
441
442
443
444
445
446
447
448
449
450
451
452
453
454
455
456
457
458
459
460
461
462
463
464
465
466
467
468
469
470
471
472
473
474
475
476
477
478
479
480
481
482
483
484
485
486
487
488
489
490
491
492
493
494
495
496
497
498
499
500
501
502
503
504
505
506
507
508
509
510
511
512
513
514
515
516
517
518
519
520
521
522
523
524
525
526
527
528
529
530
531
532
533
534
535
536
537
538
539
540
541
542
543
544
545
546
547
548
549
550
551
552
553
554
555
556
557
558
559
560
561
562
563
564
565
566
567
568
569
570
571
572
573
574
575
576
577
578
579
580
581
582
583
584
585
586
587
588
589
590
591
592
593
594
595
596
597
598
599
600
601
602
603
604
605
606
607
608
609
610
611
612
613
614
615
616
617
618
619
620
621
622
623
624
625
626
627
628
629
630
631
632
633
634
635
636
637
638
639
640
641
642
643
644
645
646
647
648
649
650
651
652
653
654
655
656
657
658
659
660
661
662
663
664
665
666
667
668
669
670
671
672
673
674
675
676
677
678
679
680
681
682
683
684
685
686
687
688
689
690
691
692
693
694
695
696
697
698
699
700
701
702
703
704
705
706
707
708
709
710
711
712
713
714
715
716
717
718
719
720
721
722
723
724
725
726
727
728
729
730
731
732
733
734
735
736
737
738
739
740
741
742
743
744
745
746
747
748
749
750
751
752
753
754
755
756
757
758
759
760
761
762
763
764
765
766
767
768
769
770
771
772
773
774
775
776
777
778
779
780
781
782
783
784
785
786
787
788
789
790
791
792
793
794
795
796
797
798
799
800
801
802
803
804
805
806
807
808
809
810
811
812
813
814
815
816
817
818
819
820
821
822
823
824
825
826
827
828
829
830
831
832
833
834
835
836
837
838
839
840
841
842
843
844
845
846
847
848
849
850
851
852
853
854
855
856
857
858
859
860
861
862
863
864
865
866
867
868
869
870
871
872
873
874
875
876
877
878
879
880
881
882
883
884
885
886
887
888
889
890
891
892
893
894
895
896
897
898
899
900
901
902
903
904
905
906
907
908
909
910
911
912
913
914
915
916
917
918
919
920
921
922
923
924
925
926
927
928
929
930
931
932
933
934
935
936
937
938
939
940
941
942
943
944
945
946
947
948
949
950
951
952
953
954
955
956
957
958
959
960
961
962
963
964
965
966
967
968
969
970
971
972
973
974
975
976
977
978
979
980
981
982
983
984
985
986
987
988
989
990
991
992
993
994
995
996
997
998
999
1000
1001
1002
1003
1004
1005
1006
1007
1008
1009
1010
1011
1012
1013
1014
1015
1016
1017
1018
1019
1020
1021
1022
1023
1024
1025
1026
1027
1028
1029
1030
1031
1032
1033
1034
1035
1036
1037
1038
1039
1040
1041
1042
1043
1044
1045
1046
1047
1048
1049
1050
1051
1052
1053
1054
1055
1056
1057
1058
1059
1060
1061
1062
1063
1064
1065
1066
1067
1068
1069
1070
1071
1072
1073
1074
1075
1076
1077
1078
1079
1080
1081
1082
1083
1084
1085
1086
1087
1088
1089
1090
1091
1092
1093
1094
1095
1096
1097
1098
1099
1100
1101
1102
1103
1104
1105
1106
1107
1108
1109
1110
1111
1112
1113
1114
1115
1116
1117
1118
1119
1120
1121
1122
1123
1124
1125
1126
1127
1128
1129
1130
1131
1132
1133
1134
1135
1136
1137
1138
1139
1140
1141
1142
1143
1144
1145
1146
1147
1148
1149
1150
1151
1152
1153
1154
1155
1156
1157
1158
1159
1160
1161
1162
1163
1164
1165
1166
1167
1168
1169
1170
1171
1172
1173
1174
1175
1176
1177
1178
1179
1180
1181
1182
1183
1184
1185
1186
1187
1188
1189
1190
1191
1192
1193
1194
1195
1196
1197
1198
1199
1200
1201
1202
1203
1204
1205
1206
1207
1208
1209
1210
1211
1212
1213
1214
1215
1216
1217
1218
1219
1220
1221
1222
1223
1224
1225
1226
1227
1228
1229
1230
1231
1232
1233
1234
1235
1236
1237
1238
1239
1240
1241
1242
1243
1244
1245
1246
1247
1248
1249
1250
1251
1252
1253
1254
1255
1256
1257
1258
1259
1260
1261
1262
1263
1264
1265
1266
1267
1268
1269
1270
1271
1272
1273
1274
1275
1276
1277
1278
1279
1280
1281
1282
1283
1284
1285
1286
1287
1288
1289
1290
1291
1292
1293
1294
1295
1296
1297
1298
1299
1300
1301
1302
1303
1304
1305
1306
1307
1308
1309
1310
1311
1312
1313
1314
1315
1316
1317
1318
1319
1320
1321
1322
1323
1324
1325
1326
1327
1328
1329
1330
1331
1332
1333
1334
1335
1336
1337
1338
1339
1340
1341
1342
1343
1344
1345
1346
1347
1348
1349
1350
1351
1352
1353
1354
1355
1356
1357
1358
1359
1360
1361
1362
1363
1364
1365
1366
1367
1368
1369
1370
1371
1372
1373
1374
1375
1376
1377
1378
1379
1380
1381
1382
1383
1384
1385
1386
1387
1388
1389
1390
1391
1392
1393
1394
1395
1396
1397
1398
1399
1400
1401
1402
1403
1404
1405
1406
1407
1408
1409
1410
1411
1412
1413
1414
1415
1416
1417
1418
1419
1420
1421
1422
1423
1424
1425
1426
1427
1428
1429
1430
1431
1432
1433
1434
1435
1436
1437
1438
1439
1440
1441
1442
1443
1444
1445
1446
1447
1448
1449
1450
1451
1452
1453
1454
1455
1456
1457
1458
1459
1460
1461
1462
1463
1464
1465
1466
1467
1468
1469
1470
1471
1472
1473
1474
1475
1476
1477
1478
1479
1480
1481
1482
1483
1484
1485
1486
1487
1488
1489
1490
1491
1492
1493
1494
1495
1496
1497
1498
1499
1500
1501
1502
1503
1504
1505
1506
1507
1508
1509
1510
1511
1512
1513
1514
1515
1516
1517
1518
1519
1520
1521
1522
1523
1524
1525
1526
1527
1528
1529
1530
1531
1532
1533
1534
1535
1536
1537
1538
1539
1540
1541
1542
1543
1544
1545
1546
1547
1548
1549
1550
1551
1552
1553
1554
1555
1556
1557
1558
1559
1560
1561
1562
1563
1564
1565
1566
1567
1568
1569
1570
1571
1572
1573
1574
1575
1576
1577
1578
1579
1580
1581
1582
1583
1584
1585
1586
1587
1588
1589
1590
1591
1592
1593
1594
1595
1596
1597
1598
1599
1600
1601
1602
1603
1604
1605
1606
1607
1608
1609
1610
1611
1612
1613
1614
1615
1616
1617
1618
1619
1620
1621
1622
1623
1624
1625
1626
1627
1628
1629
1630
1631
1632
1633
1634
1635
1636
1637
1638
1639
1640
1641
1642
1643
1644
1645
1646
1647
1648
1649
1650
1651
1652
1653
1654
1655
1656
1657
1658
1659
1660
1661
1662
1663
1664
1665
1666
1667
1668
1669
1670
1671
1672
1673
1674
1675
1676
1677
1678
1679
1680
1681
1682
1683
1684
1685
1686
1687
1688
1689
1690
1691
1692
1693
1694
1695
1696
1697
1698
1699
1700
1701
1702
1703
1704
1705
1706
1707
1708
1709
1710
1711
1712
1713
1714
1715
1716
1717
1718
1719
1720
1721
1722
1723
1724
1725
1726
1727
1728
1729
1730
1731
1732
1733
1734
1735
1736
1737
1738
1739
1740
1741
1742
1743
1744
1745
1746
1747
1748
1749
1750
1751
1752
1753
1754
1755
1756
1757
1758
1759
1760
1761
1762
1763
1764
1765
1766
1767
1768
1769
1770
1771
1772
1773
1774
1775
1776
1777
1778
1779
1780
1781
1782
1783
1784
1785
1786
1787
1788
1789
1790
1791
1792
1793
1794
1795
1796
1797
1798
1799
1800
1801
1802
1803
1804
1805
1806
1807
1808
1809
1810
1811
1812
1813
1814
1815
1816
1817
1818
1819
1820
1821
1822
1823
1824
1825
1826
1827
1828
1829
1830
1831
1832
1833
1834
1835
1836
1837
1838
1839
1840
1841
1842
1843
1844
1845
1846
1847
1848
1849
1850
1851
1852
1853
1854
1855
1856
1857
1858
1859
1860
1861
1862
1863
1864
1865
1866
1867
1868
1869
1870
1871
1872
1873
1874
1875
1876
1877
1878
1879
1880
1881
1882
1883
1884
1885
1886
1887
1888
1889
1890
1891
1892
1893
1894
1895
1896
1897
1898
1899
1900
1901
1902
1903
1904
1905
1906
1907
1908
1909
1910
1911
1912
1913
1914
1915
1916
1917
1918
1919
1920
1921
1922
1923
1924
1925
1926
1927
1928
1929
1930
1931
1932
1933
1934
1935
1936
1937
1938
1939
1940
1941
1942
1943
1944
1945
1946
1947
1948
1949
1950
1951
1952
1953
1954
1955
1956
1957
1958
1959
1960
1961
1962
1963
1964
1965
1966
1967
1968
1969
1970
1971
1972
1973
1974
1975
1976
1977
1978
1979
1980
1981
1982
1983
1984
1985
1986
1987
1988
1989
1990
1991
1992
1993
1994
1995
1996
1997
1998
1999
2000
2001
2002
2003
2004
2005
2006
2007
2008
2009
2010
2011
2012
2013
2014
2015
2016
2017
2018
2019
2020
2021
2022
2023
2024
2025
2026
2027
2028
2029
2030
2031
2032
2033
2034
2035
2036
2037
2038
2039
2040
2041
2042
2043
2044
2045
2046
2047
2048
2049
2050
2051
2052
2053
2054
2055
2056
2057
2058
2059
2060
2061
2062
2063
2064
2065
2066
2067
2068
2069
2070
2071
2072
2073
2074
2075
2076
2077
2078
2079
2080
2081
2082
2083
2084
2085
2086
2087
2088
2089
2090
2091
2092
2093
2094
2095
2096
2097
2098
2099
2100
2101
2102
2103
2104
2105
2106
2107
2108
2109
2110
2111
2112
2113
2114
2115
2116
2117
2118
2119
2120
2121
2122
2123
2124
2125
2126
2127
2128
2129
2130
2131
2132
2133
2134
2135
2136
2137
2138
2139
2140
2141
2142
2143
2144
2145
2146
2147
2148
2149
2150
2151
2152
2153
2154
2155
2156
2157
2158
2159
2160
2161
2162
2163
2164
2165
2166
2167
2168
2169
2170
2171
2172
2173
2174
2175
2176
2177
2178
2179
2180
2181
2182
2183
2184
2185
2186
2187
2188
2189
2190
2191
2192
2193
2194
2195
2196
2197
2198
2199
2200
2201
2202
2203
2204
2205
2206
2207
2208
2209
2210
2211
2212
2213
2214
2215
2216
2217
2218
2219
2220
2221
2222
2223
2224
2225
2226
2227
2228
2229
2230
2231
2232
2233
223

carbide are commonly used as the ceramic materials. The sintered bodies of alumina and zirconia are also used for bioceramics such as artificial tooth, artificial femoral head and artificial knee in view of mixing of metals into a living body, wear resistance, and the like.

The conventional raw material powder such as alumina or silicon carbide in the foregoing applications has a problem that the powder comprises fine particles whose primary particles are $0.5\ \mu\text{m}$ or less and it is non-uniform powder having a spheroidal form or having fractured surfaces. Further, the inside of each particle is also non-homogeneous and have a large number of defects. The powder has a wide particle size distribution and contains a large number of coarse aggregated particles. These cause the formation of pores in a sintering process. As a method for reducing the pores, there have been commonly a method in which several sintering agents are added. However, a sintered body with sufficiently high fired density and less pores cannot be obtained.

The ceramics sintered body product for components of a semiconductor manufacturing system is used by mirror-polishing its portion to be in contact with a silicon wafer. The ceramics sintered body product manufactured from the conventional raw material powder has problems that the wafer

is marred by foreign substances such as dust particles adhered to the pore of the sintered body, or the edge of the pore, and the like.

Further, when the silicon wafer or the like supported on the ceramics sintered body having a large number of pores is subjected to processing such as heat treatment or plasma etching, this arises a problem that there occurs falling off of particles, or elution of impurities such as Na from the ceramics in the vicinity of the pores to contaminate the wafer.

The foregoing problems have further become important with the progress of achieving higher density and higher integration of a semiconductor device. Accordingly, a sintered body with high purity and high density, and less pores has been required.

Also, in bioceramics such as artificial tooth, artificial femoral head and artificial knee, the ceramic materials or polymer materials used in a pair therewith are worn out by the edge of the pore in the polished surface. This results in the formation of fine particles to cause pain to a human body. Further, these pores become the starting points of fracture to lower the strength of the sintered body and reliability of the product.

To overcome these problems, there are disclosed plasma-resistant fluorine alumina ceramics and the

manufacturing method thereof in Japanese Laid-Open Patent Publication No. 9-2864. In Japanese Laid-Open Patent Publication No. 9-2864, silicon oxide and calcium oxide are added therein in a large amount of 0.3 to 0.7 wt% for reducing the area % of the unsintered particle. Thus, there still has a problem about the corrosion resistance in hot water, an acid solution or an alkaline solution. Further, it is generally known that a sintered body having a small number of pore can be obtained by hot isostatic press. However, there still has a problem industrially that it is required to sinter at high temperatures and high pressures.

SUMMARY OF THE INVENTION

The present inventors have found that a high purity alumina sintered body with extremely less pores can be obtained by using the specific alumina powder as a raw material and calcining said alumina in an air atmosphere, and the productivity thereof is high, and have completed the present invention.

That is, the present invention relates to (1) a process for producing a polycrystalline alumina sintered body which comprises the steps of:

subjecting alumina powder to ultrasonic irradiation, mechanical stirring not using a grinding medium, or ultrasonic irradiation and mechanical stirring not using a

grinding medium, resulting in slurry dispersed in a solvent;
drying and forming said slurry to produce a molded body;
and then

sintering said green body in an air atmosphere at a
temperature in the range of 1400 °C to 1800 °C;

wherein said alumina powder having a purity of 99.99 wt%
or more comprises a polyhedral particle having substantially
no fractured surface, and comprises α alumina particles
having polyhedral shape; a D/H ratio of from 0.5 or more to
3.0 or less, wherein D represents a maximum particle diameter
parallel to the hexagonal lattice plane of a hexagonal close
packed lattice of α alumina, and H represents a maximum
particle diameter perpendicular to the hexagonal lattice
plane of a hexagonal close packed lattice of α alumina; the
number-average particle size of from 0.1 μm or more to 1.0
 μm or less; a D90/D10 ratio of 7 or less, wherein D10 and
D90 are the particle sizes at 10 % cumulation diameter and
90 % cumulation diameter, respectively, from the smallest
particle side in a cumulative particle size distribution.

Also, the present invention relates to a process
described in (1), wherein an alumina powder added a sintering
assistant is subjected to ultrasonic irradiation,
mechanical stirring not using a grinding medium, or
ultrasonic irradiation and mechanical stirring not using a

grinding medium, resulting in a slurry dispersed in a solvent.

DETAILED DESCRIPTION OF THE INVENTION

Below, the present invention will now be described in detail.

In the present invention, alumina powder used as a raw material is alumina having a purity of 99.99 wt% or more, having substantially no fractured surface, and the residue on the sieve is in an amount of 100 ppm or less when wet sieving is performed by using a 5- μ m-mesh filter. The alumina powder comprises α alumina particles having a polyhedral shape; a D/H ratio of from 0.5 or more to 3.0 or less, preferably of from 0.8 or more to 1.5 or less, wherein D represents a maximum particle diameter parallel to the hexagonal lattice plane of a hexagonal close packed lattice of α -alumina, and H represents a maximum particle diameter perpendicular to the hexagonal lattice plane of a hexagonal close packed lattice of α -alumina. The number-average particle size of the α alumina particles is from 0.1 μ m or more to 1.0 μ m or less, preferably of from 0.2 μ m or more to 0.7 μ m or less. Further, the α alumina particles have a D90/D10 ratio of 7 or less, which is a particle size distribution, wherein D10 and D90 are the particle sizes at 10 % cumulation diameter and 90 % cumulation diameter, respectively, from the smallest particle side in a cumulative particle size distribution.

Examples of the above-described alumina powder include α alumina powder obtained by calcining transition alumina, or alumina powder which can be changed to transition alumina by heat treatment, in an atmospheric gas containing hydrogen chloride. The α alumina powder can be obtained by, for example, a method described in Japanese Laid-Open Patent Publication No. Heisei 6-191836.

When the average particle size of the primary particles of the alumina powder used as raw material exceeds $1.0 \mu\text{m}$, the degree of sintering is reduced, resulting in an increase in number of pores remaining in the sintered body. Also, when the particle size distribution is not so narrow one as described above, the arrangement of particles in the green body does not become uniform to cause the local growth of particles, resulting in an increase in number of residual pores. Further, when a purity of alumina is less than 99.99 wt%, this becomes one factor which can cause mixing of foreign substances into a semiconductor product, or allows anomalous growth of particles due to foreign substances to proceed, resulting in an increase in number of residual pores.

Also, in alumina powder with a primary particle size of $0.1 \mu\text{m}$ or less, the interaction between particles is strong to form aggregate particles, resulting in an increase in

number of pores.

As the raw material of the present invention, an average particle size of alumina primary particles is preferably from 0.2 μm or more to 0.7 μm or less.

Examples of the alumina raw material of the present invention include AA02 (primary particle size of 0.2 μm), AA03 (primary particle size of 0.3 μm), AA04 (primary particle size of 0.4 μm), and AA07 (primary particle size of 0.7 μm), of SUMICORUNDUM manufactured by Sumitomo Chemical Co., Ltd. All of the purities thereof are 99.99 wt% or more.

Further, when the alumina powder used as a raw material has a purity of 99.99 wt% or more, said alumina powder may contain oxides or salts of elements other than aluminum in an amount of less than 0.01 wt%, or the substances such as water, organic substances and halogen elements in an amount of less than 1 parts by weight which are not spoiling the properties of the alumina sintered body of the present invention, and which can be removed from the raw material by heating at 1000 $^{\circ}\text{C}$ or less.

By using the above-described high purity alumina powder as a raw material, uniform arrangement of particles in the

green body, high fired density , and uniform proceeding of growth of the particles in the whole sintered body can be achieved. This reduces pores to be left behind in the sintered body grains, or the grain boundaries. Further, local anomalous growth of particles due to impurities in the rawmaterial will not proceed, and hence pores will not remain. Consequently, a high fired density of 3.970 g/cm^2 or more can be obtained. Further, a sintering agent is added if required for achieving still higher fired density. This inhibits the growth of grain boundary at the final stage of sintering to remove pores. As a result of such an effect and the like, a sintered body with a high fired density of 3.975 g/cm^3 or more can be obtained.

Examples of the sintering agent include one or more compounds selected from the group consisting of alkaline earth metal compounds and silicon compounds. Examples of the alkaline earth metal compound and silicon compound include oxides, nitrates, acetates, hydrides, chlorides, and alkoxides thereof. However, they are not limited thereto as long as they become oxides at a temperature of 1200°C or less during sintering in an atmosphere. Concrete examples of the alkaline earth metal include Mg, Ca, Sr, and Ba. As the sintering agent , a magnesium compound is preferable, and magnesium nitrate is particularly preferable. The amount

thereof to be added is generally from 10 ppm or more to 2000 ppm or less in terms of oxides, and preferably from 10 ppm or more to 700 ppm or less. Each of the above-described compounds becomes oxide during sintering in an atmosphere, and exerts its effect as sintering agent. When a sintered body with an alumina purity of 99.99 wt% or more is required depending upon its use, the sintering agent is added to the alumina powder in an amount of from 10 ppm or more to 150 ppm or less, more preferably of from 10 ppm or more to 70 ppm or less, in terms of oxide.

The process for producing a slurry will now be described below. First, the above-described alumina raw material powder, a solvent, and a dispersant are blended in appropriate amounts with mechanical stirring and mixing. In this step, there have been commonly and widely used the mixing methods using grinding media, i.e., the grinding methods using devices generally referred to as ball mill, vibration mill, pearl mill, attriter, and the like. However, the slurry production method of the present invention is characterized in that the alumina powder used as a raw material in the present invention undergoes less aggregates, and has uniform particle shape and particle size. Accordingly, the alumina powder can be dispersed to form a uniform slurry by irradiating with ultrasonic wave from the outside using a ultrasonic bath, or

irradiating with ultrasonic wave by means of a ultrasonic homogenizer. The dispersion method not using medium such as ceramics ball is preferred in terms of avoiding mixing of oxides or salts other than aluminum. As for the ultrasonic wave, the irradiation ability is preferably 10 kHz or more, more preferably 25 kHz or more, in the case of a bath volume of 40 liters. The stirring and mixing time varies depending upon the volume of the slurry. For example, when the amount of slurry is 10 liters, stirring and mixing is preferably performed for 30 minutes or more. The raw material powder is sufficiently dispersed, and then organic binder is mixed therein. For example, when the amount of slurry is 10 liters, the mixing is preferably performed for one hour or more. It suffices only to perform mechanical stirring using an agitating blade even without ultrasonic irradiation.

The slurry prepared as described above can properly be deaerated under reduced pressure. Alternatively, various kinds of defoaming agents can also be used. Further, in accordance with the subsequent forming method, the viscosity may properly be set to be in the range of 50 to 10000 mPa/s by addition of various kinds of pH adjusters and flocculating agents. For example, in granulation by a spray dryer, the viscosity of the alumina slurry is preferably adjusted to be in the range of 300 to 400 mPa/s by pH adjustment with an

aqueous solution of hydrochloric acid, aqueous ammonia, and the like for producing spherical granules. Further, the alumina concentration in the slurry can be increased by standing settling, centrifugal separation, and vacuum concentration by means of a rotary evaporator, and the like .

As a solvent, it varies depending upon the kind of binder to be used and the forming method. For polyvinyl alcohol and acrylic binder to be used when granules are produced by a spray dryer, water is most preferable. Various kinds of organic solvents can also be used according to the formulation. For example, a mixed solvent of toluene and butanol is preferable in doctor blade forming(also called tape casting).

As a dispersant, ammonium salt of polycarboxylic acid [ex., tradename; SN-D5468, manufactured by San Nopco Co., Ltd.] is mainly used when the solvent is water. For organic solvent, ethyl oleate, sorbitan monooleate, sorbitan trioleate, polycarboxylic acid series , and the like are used. For the alumina raw material powder to be used as raw material in the present invention, polyester series [tradename; TEXAPHOR 3012, manufactured by San Nopco Co., Ltd.] is preferable, but is not limited to these examples. The method not using a dispersant can provide a slurry with lower viscosity depending upon the organic binder to be used

together.

Examples of the organic binder include polyvinyl alcohol, polyvinyl acetal, various kinds of acrylic polymers, methyl cellulose, polyvinyl acetate, polyvinyl butyral series, various kinds of waxes, and various kinds of polysaccharides, but is not limited to these examples.

The plasticizer varies depending upon the organic binder to be used. Examples thereof include ethylene glycol, diethylene glycol, polyethylene glycol, glycerin, polyglycerin, and various kinds of esters. Especially when an organic solvent is used, dibutyl phthalate, diethylhexyl phthalate and the like are used, but is not limited to these examples.

In the present invention, a mold-releasing agent, flocculating agent, pH adjuster can also be added as other additives. However, it is important that there are no inorganic impurities other than aluminium in solvents and additives. No addition of organic substances is most preferable as long as it presents no obstacles to shape retention of the green body, and handling on processing.

Examples of the forming means after drying the slurry

include conventional methods such as slip casting ,
pressurized slip casting , centrifugal casting , doctor blade
forming , and extrusion forming. Alternatively, granules
are produced by means of a spray dryer, or various kinds of
pelletizing machines, after which dry forming methods such
as pressing methods and cold isostatic press can be employed.

For the cold isostatic press , the above-described
slurry is formed into granule by spray dry, or the like. The
resulting granule is uniaxially pressed, preferably under a
pressure in the range of 50 to 500 kg/cm², more preferably
under a pressure in the range of 200 to 300 kg/cm². Thereafter,
the resulting body is isotropically applied with a pressure
preferably in the range of 0.5 to 3 t/cm², and more preferably
in the range of 0.8 to 1.5 t/cm² by means of a cold isostatic
press. Then, the resulting green body is processed into a
prescribed form.

Alternatively, for example, for a small green body with
a size of 20 mm or less, the raw material alumina powder can
also be charged into a mold to carry out uniaxial press, or
cold isostatic press under the above-described pressure.

The green bodies obtained by the above-described
methods are subjected to the following process depending upon
the size thereof. For example, for a green body 300 mmΦ

in diameter, and 30 mm in thickness, it is calcinated at temperatures in the range of 500 to 1000 °C for 1 hour or more, and preferably in the range of 800 to 900 °C for 3 hours or more, to be removed organic materials. Thereafter, the resulting body is sintered in an air atmosphere at a temperature in the range of 1400 to 1800 °C for 1 hour or more, and preferably for 3 hours or more. Specifically, when the primary particle of the alumina raw material powder has a size of 0.7 μm , the sintering temperature is preferably 1650 °C or more. When the primary particle has a size of 0.2 μm , it is preferably 1450 °C or more.

The maximum pore diameter of pores in the sintered body obtained by the present invention is preferably 10 μm or less. The number of pores with a size of from 1 μm or more to 10 μm or less per one mm^2 is preferably 20 or less, more preferably 10 or less. Such high fired density of alumina sintered body can be obtained. In the alumina sintered body of the present invention, there less occur falling off of particles, and elution in the vicinity of pores during use as a component of a semiconductor manufacturing system on a thermal diffusion furnace, plasma etching process, or CVD system due to the low numbers of the pores. Further, the sintered body of the present invention has good corrosion resistance as a member to be in contact with a corrosive

solution or gas. Further, there can be provided products with high reliability in terms of strength and wear resistance as bioceramic member of artificial tooth, artificial femoral head, and the like, mechanical components of bearing, thread guide, roller for rolling, pump component, and the like, and structural components of frame rod, core tube, shaft enclosing tube, and the like, owing to the low numbers of pores which are defects. Moreover, there can be provided decorative members such as plates and cups excellent in surface smoothness owing to no scattering of light due to pores.

Examples

Next, a description will now be given to the examples of the present invention, which is not construed as limiting the scope of the invention.

It is noted that various kinds of measurements in the present invention were carried out in the following manner.

(1) Measurement of number-average particle size of primary particles, and measurement of D/H of the primary particles

The photographs of the powder particles were taken by means of a scanning electron microscope (SEM: manufactured by JEOL, Ltd. T-300 type). Fifty to hundred particles were

selected from the photographs to conduct the image analysis thereof, thereby determining the values as the mean values.

(2) Measurement of D10 and D90 (measurement of weight cumulative particle size distribution; abbreviated as "particle size distribution")

Measurement was carried out by means of a master sizer (manufactured by Malvern Co.,) by a laser diffraction scattering method. Alumina slurry for the measurement was prepared in the following manner. That is, 25 g of 0.5 wt% aqueous solution of sodium hexametaphosphate was added to 2.5 g of alumina powder. The resulting mixed solution was irradiated with ultrasonic wave by a homogenizer for 2 minutes to prepare the alumina slurry.

(3) Wet sieving

One kg of distilled water was added to one kg of alumina. Then, the resulting mixture was irradiated with ultrasonic wave with stirring for 30 minutes in a ultrasonic bath with a volume of 6 liters (frequency: 28 kHz, output: 200 W) to prepare a slurry. In a beaker filled with distilled water, 5 μ m nylon mesh in bag form was immersed. The total amount of the alumina slurry previously prepared was flown into the nylon bag. Then, the whole beaker was irradiate with ultrasonic wave using a ultrasonic bath. This causes the alumina particles to pass through the nylon mesh and move into

the beaker. Twenty minutes later, the nylon mesh bag was pulled up, and the outside of the bag was washed sufficiently, and dried to determine the amount of increase in weight. The amount of increase in weight was divided by the alumina charge of 1 kg, and the obtained value was taken as residue on the 5- μ m sieve.

(4) Measurement of the number of pores and pore size on the polished surface of alumina sintered body

The number of pores was determined as follows: that is, the photograph (magnification: 50 times) of the mirror-polished surface of a sintered body was taken using a light microscope (manufactured by Olympus Optical Co., Ltd.; BH-2). The number of pores occurring as black points in the photograph were counted visually to be converted into the number per mm^2 . The alumina sintered body was first subjected to coarse grinding with a #800 diamond grinding wheel, resulting in a plane surface. Thereafter, the mirror polishing was carried out using 3- μ m polycrystalline diamond slurry and a copper table polishing machine (high press lapping system manufactured by NIHON ENGIS Co.). Polishing was carried out for 60 minutes or more with the surface pressure during polishing being set at 300 g/cm^2 or more. For removing scratches on the surface, polishing was further conducted for 30 minutes or more with 1- μ m polycrystalline diamond slurry.

For a pore of not a circular shape, but of elliptical or indefinite shape, the measurement of the pore size was carried out taking the maximum diameter or the major axis of the diagonal line of the pore as pore size.

(6) Measurement of fired density of an alumina sintered body

The fired density of a sintered body was measured according to the Archimedes method.

(7) Corrosion test

The corrosion test was carried out as follows: that is, the sintered body with its surface polished obtained by the above-described method was immersed in 80 °C nitric acid for 50 hours. Then, the pore on the surface was observed under light microscope to determine the amount of increase in area of the pore by means of an image analysis apparatus.

(8) Analysis of purity of alumina sintered body (ICP-AES quantitative determination method)

The alumina sintered body was ground in a boron nitride mortar, followed by alkali fusion. The fused material was subjected to ICP emission spectral analysis (ICP quantometer SPS1200VR type manufactured by Seiko Electronic Industry Co., Ltd.).

Example 1

In this example 1, α alumina powder (tradename SUMICORUNDUM AA04) manufactured by Sumitomo Chemical Co. Ltd., was used as raw material. The alumina powder is comprised of polyhedral particles each substantially not having a fractured surface and having 8 to 20 phases. The primary particle size thereof determined from the SEM photograph was found to be $0.4\ \mu\text{m}$. From the results of the particle size distribution measurement, D90 was found to be $1.48\ \mu\text{m}$, D10 was found to be $0.31\ \mu\text{m}$, and D90/D10 was found to be 4.8. The residue on the sieve of wet sieving was found to be in an amount of 5 ppm.

Five kg of the alumina powder AA04, 3 kg of water (solvent), and 62.5 g of a dispersant, ammonium polycarboxylate [manufactured by San Nopco Co, Ltd.; tradename SN-D5468] were mixed with stirring for 30 minutes while being irradiated with ultrasonic wave. Then, 750 g of 10 wt% solution of polyvinyl alcohol (manufactured by Kuraray Corp.; tradename PVA205c) as organic binder, 25 g of polyethylene glycol (reagent; degree of polymerization 400) as plasticizer, and 140 g of stearic acid emulsion [manufactured by CHUKYO YUSHI Co., Ltd; tradename CELOSOL 920] as lubricant were added in total amounts simultaneously,

followed by 60-min of stirring and mixing, resulting in a slurry.

To the resulting slurry, was added 110 ml of 1N aqueous solution of hydrochloric acid to adjust the viscosity to 350 cP. The thus prepared slurry was subjected to spray drying by means of a spray dryer to produce granules. The resulting granule powder was charged into a mold, which was then formed under a load of 1500 kg/cm² by means of a uniaxial press machine. This resulted in a cylindrical green body with a diameter of 20 mm and a height of 10 mm. Then, the green body thus produced was removed organic materials at 900 °C for 3 hours, followed by sintering in an atmosphere at 1650 °C for 2 hours.

The density of the sintered body was found to be 3.974 g/cm³. There was observed no pore with a size of more than 10 μm, and the number of pores each with a maximum diameter between 1 μm and 10 μm, both inclusive, was found to be 12 per mm², on the mirror-polished surface of the sintered body.

It was also found that, the amounts of the impurities of the sintered body were as follows: Fe: 5 ppm, Si: 5 ppm, Ca ≤ 1 ppm, Mg ≤ 1 ppm, Na ≤ 5 ppm, and other elements : less than the amount of detection limit (less than 1 ppm), and the total amount of elements other than Al: less than 50 ppm.

The pore occupied area after the corrosion test was found

to be 0.02 %.

Example 2

One hundred g of the alumina powder AA04 of example 1, 60 g of water, and 1.3 g of a dispersant SN-D5468 were mixed with stirring for 30 minutes while being irradiated with ultrasonic wave.

The resulting slurry was allowed to stand under reduced pressure for 30 minutes, to be deaerated. Further, a green body 30 mm wide, 50 mm long and 5 mm high was produced by slip casting utilizing a plaster mold. The resulting green body was sintered at 1650 °C for 2 hour.

The density of the sintered body was found to be 3.977 g/cm³. There was observed no pore with a size of more than 10 μm, and the number of pores each with a maximum diameter between 1 μm and 10 μm, both inclusive, was found to be 18 per mm², on the mirror-polished surface of the sintered body.

It was also found that, the amounts of the impurities of the sintered body were as follows: Fe: 9 ppm, Si: 5 ppm, Ca ≤ 1 ppm, Mg ≤ 1 ppm, Na ≤ 5 ppm, and other elements : less than the amount of detection limit (less than 1 ppm), and the total amount of elements other than Al: less than 50 ppm.

The pore occupied area after the corrosion test was found

to be 0.02 %.

Example 3

In this example 3, α alumina powder (tradename SUMICORUNDUM AA02) manufactured by Sumitomo Chemical Co., Ltd., was used as raw material. The alumina powder is comprised of polyhedral particles each substantially not having a fractured surface and having 8 to 20 phases. The primary particle size thereof determined from the SEM photograph was found to be 0.2 μm . From the results of the particle size distribution measurement, D90 was found to be 1.08 μm , D10 was found to be 0.18 μm , and D90/D10 was found to be 6.0. The residue on the sieve of wet sieving was found to be in an amount of 5 ppm.

Granules were produced under the same conditions as those in example 1, except that the alumina powder AA02 was used as raw material. A cylindrical green body was produced from the granules under the same conditions as those in example 1. Then, the green body thus produced was removed organic materials at 900 °C for 3 hours, followed by sintering in an atmosphere at 1550 °C for 2 hours.

The density of the sintered body was found to be 3.975 g/cm³. There was observed no pore with a size of more than

10 μm , and the number of pores each with a maximum diameter between 1 μm and 10 μm , both inclusive, was found to be 15 per mm^2 , on the mirror-polished surface of the sintered body.

It was also found that, the amounts of the impurities of the sintered body were as follows: Fe: 6 ppm, Si: 9 ppm, $\text{Ca} \leq 1$ ppm, $\text{Mg} \leq 1$ ppm, $\text{Na} \leq 5$ ppm, and other elements : less than the amount of detection limit (less than 1 ppm), and the total amount of elements other than Al: less than 50 ppm.

The pore occupied area after the corrosion test was found to be 0.02 %.

Example 4

In this example 4, α alumina powder (tradename SUMICORUNDUM AA03) manufactured by Sumitomo Chemical Co., Ltd., was used as raw material. The alumina powder is comprised of polyhedral particles each substantially not having a fractured surface and having 8 to 20 phases. The primary particle size thereof determined from the SEM photograph was found to be 0.33 μm . From the results of the particle size distribution measurement, D90 was found to be 1.38 μm , D10 was found to be 0.26 μm , and D90/D10 was found to be 5.0. The residue on the sieve of wet sieving was found to be in an amount of 10 ppm.

The alumina powder whose primary particle size was 0.33

μm was charged into a mold, which was then formed under a load of 200 kg/cm^2 by means of a uniaxial press machine. This resulted in a cylindrical green body with a diameter of 20 mm and a height of 10 mm. Then, the green body thus produced was subjected to cold isostatic press under a pressure of 1.0 t/cm^2 . The green body was defatted at $900\text{ }^\circ\text{C}$ for 3 hours, followed by sintering in an atmosphere at $1600\text{ }^\circ\text{C}$ for 2 hours.

The density of the sintered body was found to be 3.980 g/cm^3 . There was observed no pore with a size of more than $10\text{ }\mu\text{m}$, and the number of pores each with a maximum diameter between $1\text{ }\mu\text{m}$ and $10\text{ }\mu\text{m}$, both inclusive, was found to be 5 per mm^2 , on the mirror-polished surface of the sintered body.

It was also found that, the amounts of the impurities of the sintered body were as follows: Si: 8 ppm, Na ≤ 5 ppm, and other elements : less than the amount of detection limit (less than 1 ppm), and the total amount of elements other than Al: less than 50 ppm.

The pore occupied area after the corrosion test was found to be 0.01 %.

Example 5

In this example 5, α alumina powder (tradename SUMICORUNDUM AA07) manufactured by Sumitomo Chemical Co. Ltd., was used as raw material. The alumina powder is comprised

of polyhedral particles each substantially not having a fractured surface and having 8 to 20 phases. The primary particle size thereof determined from the SEM photograph was found to be $0.7\ \mu\text{m}$. From the results of the particle size distribution measurement, D90 was found to be $2.08\ \mu\text{m}$, D10 was found to be $0.57\ \mu\text{m}$, and D90/D10 was found to be 3.6. The residue on the sieve of wet sieving was in an amount of 4 ppm.

Five kg of the alumina powder AA07, 3 kg of water, and 62.5 g of a dispersing agent, SN-D5468 were mixed with stirring for 30 minutes while being irradiated with ultrasonic wave. Then, 250 g of 40 wt% solution of acrylic emulsion [manufactured by Dainippon Ink & Chemicals Inc.; tradename BONCOAT3981] as organic binder, 140 g of CELOSOL 920 as lubricant were added in total amounts simultaneously, followed by 60-min of stirring and mixing, resulting in a slurry.

Granules and a molded body were produced under the same conditions as those in example 1, except that the resulting slurry was used. Then, the green body was removed organic materials at $900\ ^\circ\text{C}$ for 3 hours, followed by sintering in an atmosphere at $1750\ ^\circ\text{C}$ for 2 hours.

The density of the sintered body was found to be 3.971 g/cm³. There was observed no pore with a size of more than 10 μ m, and the number of pores each with a maximum diameter between 1 μ m and 10 μ m, both inclusive, was found to be 15 per mm², on the mirror-polished surface of the sintered body.

It was also found that, the amounts of the impurities of the sintered body were as follows: Fe: 10 ppm, Na \leq 5 ppm, and other elements : less than the amount of detection limit (less than 1 ppm), and the total amount of elements other than Al: less than 50 ppm. The pore occupied area after the corrosion test was found to be 0.02 %.

Example 6

In the process of producing the slurry of example 4, 6.4 g (200 ppm in terms of MgO) of magnesium nitrate hexahydrate (reagent grade) was added as sintering agent. Granules and a green body were produced under the same conditions as those in example 4. Then, the green body was removed organic materials at 900 °C for 3 hours, followed by sintering in an atmosphere at 1550 °C for 2 hours.

The density of the sintered body was found to be 3.984 g/cm³. There was observed no pore with a size of more than 10 μ m, and the number of pores each with a maximum diameter between 1 μ m and 10 μ m, both inclusive, was found to be 7

per mm², on the mirror-polished surface of the sintered body.

The pore occupied area after the corrosion test was found to be 0.02 %.

It was also found that, the amounts of the impurities of the sintered body were as follows: Fe: 5 ppm, Si: 5 ppm, Ca \leq 1 ppm, Mg: 125 ppm, Na \leq 5 ppm, and other elements : less than the amount of detection limit (less than 5 ppm), and the total amount of elements other than Al: less than 170 ppm.

Example 7

In the process of producing the slurry of example 1, 16.0 g (500 ppm in terms of MgO) of magnesium nitrate hexahydrate (reagent grade) was added as sintering agent. Granules and a green body were produced under the same conditions as those in example 1. Then, the green body was removed organic materials at 900 °C for 3 hours, followed by sintering in an atmosphere at 1600 °C for 2 hours.

The density of the sintered body was found to be 3.982 g/cm³. There was observed no pore with a size of more than 10 μ m, and the number of pores each with a maximum diameter between 1 μ m and 10 μ m, both inclusive, was found to be 4 per mm², on the mirror-polished surface of the sintered body.

The pore occupied area after the corrosion test was

found to be 0.01 %.

It was also found that, the amounts of the impurities of the sintered body were as follows: Fe: 9 ppm, Si: 8 ppm, Ca \leq 1 ppm, Mg: 305 ppm, Na \leq 5 ppm, and other elements : less than the amount of detection limit (less than 1 ppm), and the total amount of elements other than Al: less than 350 ppm.

Example 8

In the process of producing the slurry of example 3, 1.6 g(50 ppm in terms of MgO) of magnesium nitrate hexahydrate (reagent grade) was added as sintering agent. Granules and a green body were produced under the same conditions as those in example 3. Then, the green body was removed organic materials at 900 °C for 3 hours, followed by sintering in an atmosphere at 1600 °C for 2 hours.

The density of the sintered body was found to be 3.982 g/cm³. There was observed no pore with a size of more than 10 μ m, and the number of pores each with a maximum diameter between 1 μ m and 10 μ m, both inclusive, was found to be 5 per mm², on the mirror-polished surface of the sintered body.

The pore occupied area after the corrosion test was found to be 0.01 %.

It was also found that, the amounts of the impurities

of the sintered body were as follows: Fe: 9 ppm, Si: 8 ppm, Ca \leq 1 ppm, Mg: 25 ppm, Na \leq 5 ppm, and other elements : less than the amount of detection limit (less than 1 ppm), and the total amount of elements other than Al: less than 50 ppm.

Example 9 (Slip casting)

One hundred g of the α alumina powder AA04 of example 1, 60 g of water, 1.3 g of a dispersing agent SN-D5468, and 0.01 g of MgO (manufactured by Ube Material Co., Ltd; tradename 500A) were mixed with stirring for 30 minutes while being irradiated with ultrasonic wave. The MgO was to flow into a plaster mold in about half amount during slip casting, and hence MgO was added in an amount of 1000 ppm, corresponding to twice the amount thereof added.

The resulting slurry was allowed to stand under reduced pressure for 30 minutes, to be deaerated. Further, a greenbody 30 mm wide, 50 mm long and 5 mm high was produced by slip casting utilizing a plaster mold. The resulting green body was sintered at 1600 °C for 2 hour.

The density of the sintered body was found to be 3.983 g/cm³. There was observed no pore with a size of more than 10 μ m, and the number of pores each with a maximum diameter between 1 μ m and 10 μ m, both inclusive, was found to be 4

per mm², on the mirror-polished surface of the sintered body.

The pore occupied area after corrosion test was found to be 0.02 %.

It was also found that, the amounts of the impurities of the sintered body were as follows: Fe: 5 ppm, Si: 12 ppm, Ca: 5 ppm, Mg: 305 ppm, Na \leq 5 ppm, and other elements : less than the amount of detection limit (less than 5 ppm), and the total amount of elements other than Al: less than 350 ppm.

Example 10

In the process of producing the slurry of example 7, the amount of magnesium nitrate hexahydrate to be added as sintering agent was changed to 32.0 g (1000 ppm in terms of MgO) to produce granules. Then, a green body and further a sintered body were produced in the same manner as in example 7.

The density of the sintered body was found to be 3.980 g/cm³. There was observed no pore with a size of more than 10 μ m, and the number of pores each with a maximum diameter between 1 μ m and 10 μ m, both inclusive was found to be 5 per mm², on the mirror-polished surface of the sintered body.

The pore occupied area after the corrosion test was found to be 0.01 %.

It was also found that, the amounts of the impurities

of the sintered body were as follows: Fe: 5 ppm, Si: 8 ppm, Ca \leq 1 ppm, Mg: 600 ppm, Na \leq 5 ppm, and other elements : less than the amount of detection limit (less than 5 ppm), and the total amount of elements other than Al: less than 650 ppm.

Example 11 (Doctor blade forming also called tape casting)

In this example 11, α alumina powder (tradename SUMICORUNDUM AA05) manufactured by Sumitomo Chemical Co., Ltd., was used as raw material. The alumina powder is comprised of polyhedral particles each substantially not having a fractured surface and having 8 to 20 phases. The primary particle size thereof determined from the SEM photograph was found to be 0.5 μ m. From the results of the particle size distribution measurement, D90/D10 was found to be 4.5. The residue on the sieve of wet sieving was in an amount of 3 ppm.

Five hundred g of AA05, 0.25 g of MgO, 308 g of toluene, 90 g of ethanol, 43 g of cyclohexanone, and 10 g of polyester dispersant (manufactured by San Nopco Co., Ltd.; tradename TEXAPHOR 3112) were mixed for 16 hours in a ball mill. Further, 36 g of polyvinyl butyral (manufactured by Sekisui Chemical Co., Ltd: tradename BL-S) and 18 g of dibutyl phthalate were added and mixed for 6 hours in a ball mill to obtain a homogeneous slurry. The viscosity of the slurry was

adjusted by solvent removal, followed by film forming according to a doctor blade forming.

The resulting film was dried in air at room temperature for 96 hours, and then was cut into pieces each with a prescribed size. The resulting piece was calcined in an air atmosphere in an electric furnace. Then, the calcined body was defatted at 500 °C for 1 hour, followed by sintering at 1550 °C for 1 hour.

The density of the sintered body was found to be 3.982 g/cm³. There was observed no pore with a size of more than 10 μm, and the number of pores each with a maximum diameter between 1 μm and 10 μm, both inclusive was found to be 6 per mm², on the mirror-polished surface of the sintered body.

The pore occupied area after the corrosion test was found to be 0.02 %.

It was also found that, the amounts of the impurities of the sintered body were as follows: Fe: 5 ppm, Si: 8 ppm, Ca ≤ 1 ppm, Mg: 305 ppm, Na ≤ 5 ppm, and other elements : less than the amount of detection limit (less than 1 ppm), and the total amount of elements other than Al: less than 350 ppm.

Example 12

In the process of producing the slurry of example 5, 3.6

g (100 ppm in terms of MgO) of magnesium nitrate hexahydrate was added as sintering agent to produce a slurry. Granules and a molded body were produced in the same manner as in example 5. Then, the green body was removed organic materials at 900 °C for 3 hours, followed by sintering in an atmosphere at 1700 °C for 2 hours.

The density of the sintered body was found to be 3.980 g/cm³. There was observed no pore with a size of more than 10 μm, and the number of pores each with a maximum diameter between 1 μm and 10 μm, both inclusive, was found to be 6 per mm², on the mirror-polished surface of the sintered body.

The pore occupied area after the corrosion test was found to be 0.01 %.

It was also found that, the amounts of the impurities of the sintered body were as follows: Fe: 5 ppm, Na ≤ 5 ppm, Mg: 60 ppm, and other elements: less than the amount of detection limit (less than 1 ppm), and the total amount of elements other than Al: less than 110 ppm.

Example 13

A green body and a sintered body were produced in the same manner as in example 7, except that the amount of magnesium nitrate hexahydrate added as sintering agent was changed to 3.6 g (50 ppm in terms of MgO) to produce granules

in example 7.

The density of the sintered body was found to be 3.981 g/cm³. There was observed no pore with a size of more than 10 μ m, and the number of pores each with a maximum diameter between 1 μ m and 10 μ m, both inclusive, was found to be 7 per mm², on the mirror-polished surface of the sintered body.

The pore occupied area after the corrosion test was found to be 0.01 %.

It was also found that, the amounts of the impurities of the sintered body were as follows: Fe: 5 ppm, Si: 8 ppm, Ca \leq 1 ppm, Mg: 35 ppm, Na \leq 5 ppm, and other elements : less than the amount of detection limit (less than 1 ppm), and the total amount of elements other than Al: less than 80 ppm.

Example 14

A green body and a sintered body were produced in the same manner as in example 7, except that the amount of magnesium nitrate hexahydrate added as sintering agent was changed to 1.8 g (25 ppm in terms of MgO) to produce granules in example 7.

The density of the sintered body was found to be 3.982 g/cm³. There was observed no pore with a size of more than 10 μ m, and the number of pores each with a maximum diameter between 1 μ m and 10 μ m, both inclusive, was found to be 4

per mm², on the mirror-polished surface of the sintered body.

The pore occupied area after the corrosion test was found to be 0.01 %.

It was also found that, the amounts of the impurities of the sintered body were as follows: Fe: 5 ppm, Si: 8 ppm, Ca \leq 1 ppm, Mg: 20 ppm, Na \leq 5 ppm, and other elements : less than the amount of detection limit (less than 1 ppm), and the total amount of elements other than Al: less than 70 ppm.

Comparative Example 1 (Slip casting)

In this comparative example 1, alumina raw material powder [manufactured by Showa Denko K. K.; UA5055] of which the purity is 99.99 wt% and the primary particle size is 0.3 μ m was used. The primary particle of the alumina powder is a particle not of polyhedral shape, but of indefinite shape. The D/H was found to be larger than 2. From the observation of the particle by a tunnel electron microscope, it was found that the particle had a large number of defects within the particle. From the results of the particle size distribution measurement, D90 was found to be 2.55 μ m, D10 was found to be 0.44 μ m, and D90/D10 was found to be 5.8. The residue on the sieve of wet sieving was found to be in an amount of 120 ppm.

One hundred g of the alumina powder, 60 g of water, and 1.3 g of a dispersant SN-D5468 were mixed with stirring for 30 minutes while being irradiated with ultrasonic wave. The resulting slurry was used to carry out forming and sintering under the same conditions as in example 2.

The density of the sintered body was found to be 3.935 g/cm³. There was observed 65 pores each with a size of more than 10 μ m per mm², and an infinite number of pores each with a maximum size of 10 μ m, or less, on the mirror-polished surface of the sintered body.

Comparative Example 2

Five kg of the alumina powder UA5055 of the comparative example 1, 3 kg of water, and 65 g of a dispersant SN-D5468 were mixed with stirring for 30 minutes while being irradiated with ultrasonic wave. The resulting slurry was subjected to a ball mill treatment by means of a 2 mm Φ alumina ball. The ball milling time was set at 2 hours. Further, 1000 g of 10wt% solution of PVA205c as organic binder, and 140 g of lubricant Cellosol 920 were added in total amounts simultaneously, followed by 60-min of stirring and mixing. This resulted in a slurry.

The resulting slurry was used to produce granules and the green body under the same conditions as those in example 1. Then, the green body was sintered under the same

conditions as in example 1.

The density of the sintered body was found to be 3.945 g/cm³. There was observed 50 pores each with a size of more than 10 μ m per mm², and an infinite number of pores each with a maximum size of 10 μ m, or less, on the mirror-polished surface of the sintered body.

Comparative Example 3

Five g of the alumina powder UA5055 of the comparative example 1 was charged into a mold, which was then formed under a load of 300 kg/cm² by means of a uniaxial press machine. This resulted in a cylindrical green body with a diameter of 20 mm and a height of 10 mm. Then, the green body thus produced was subjected to cold isostatic press under a pressure of 3.0 t/cm². The green body obtained was defatted at 900 °C for 3 hours, followed by sintering in an atmosphere at 1750 °C for 2 hours.

The density of the sintered body was found to be 3.950 g/cm³. There was observed 35 pores each with a size of more than 10 μ m per mm², and an infinite number of pores each with a maximum size of 10 μ m, or less, on the mirror-polished surface of the sintered body.

Comparative Example 4

Granules and the green body were produced in the same manner as in example 7, except that the alumina powder UA5055 of the comparative example 1 was used as raw material. Then, sintering was carried out at 1550 °C for 2 hours.

The density of the sintered body was found to be 3.972 g/cm³. There was observed 34 pores each with a size of more than 10 μ m per mm², and an infinite number of pores each with a maximum size of 10 μ m, or less, on the mirror-polished surface of the sintered body.

The pore occupied area after the corrosion test was found to be 0.5 %.

Comparative Example 5

In this comparative example 5, α alumina powder (tradename; SUMICORUNDUM AA2) manufactured by Sumitomo Chemical Co. Ltd., was used as raw material. The alumina powder is comprised of polyhedral particles each substantially not having a fractured surface and having 8 to 20 phases. The primary particle size thereof determined from the SEM photograph was found to be 2 μ m. From the results of the particle size distribution measurement, D90 was found to be 2.08 μ m, D10 was found to be 0.57 μ m, and D90/D10 was found to be 3.6. The residue on the sieve of wet sieving was in an amount of 50 ppm. Granules and the green body were produced in the same manner as in example 7 using the alumina

powder of this comparative example, followed by sintering at 1700 °C for 2 hours.

The density of the sintered body was found to be 3.900 g/cm³. There was observed 46 pores each with a size of more than 10 μm per mm², and an infinite number of pores each with a maximum size of 10 μm, or less, on the mirror-polished surface of the sintered body.

The pore occupied area after the corrosion test was found to be 0.7 %.

Comparative Example 6

The alumina powder AA04 of the example 1 was subjected to heat treatment at 1400 °C. The primary particle of this alumina is a polyhedron, which aggregates on heat treatment. The D90/D10 of the particle size distribution was found to be 10.

The residue on the sieve of wet sieving was found to be in an amount of 209 ppm. Granules, the green body, and the sintering body were produced in the same manner as in example 7, except that the alumina powder of this comparative example was used as raw material.

The density of the sintered body was found to be 3.900 g/cm³. There was observed 69 pores each with a size of more than 10 μm per mm², and an infinite number of pores each with a maximum size of 10 μm, or less, on the mirror-polished

surface of the sintered body.

The pore occupied area after the corrosion test was found to be 0.9 %.

Comparative Example 7

In this comparative example 7, Bayer process alumina powder of which the purity is 99.99 wt% and the primary particle size is 0.6 μm was used as raw material. The primary particle of the alumina powder is a particle not of polyhedral shape, but of indefinite shape. The D/H was found to be larger than 3. For the particle size distribution, D90/D10 was found to be 6.6. The residue on the sieve of wet sieving was found to be in an amount of 790 ppm. Granules, the molded body, and the sintered body were produced in the same manner as in example 7, except that the alumina powder of this comparative example was used as raw material.

The density of the sintered body was found to be 3.870 g/cm³. There was observed a large number of pores each with a size of more than 10 μm on the mirror-polished surface.

The pore occupied area after the corrosion test was found to be 2.1 %.

Comparative Example 8

In this comparative example 8, an organoaluminium compound was hydrolyzed to prepare aluminium hydride,

followed by sintering at 1000 °C. The resulting alumina powder of which the purity is 99.99 wt% and the primary particle size is 0.5 μm was used as raw material. The primary particle of the alumina powder is a particle not of polyhedral shape, but of indefinite shape. The D/H was found to be 5. For the cumulative particle size distribution of the alumina powder, D90/D10 was found to be 5.8. Wet sieving was impossible. Granules, and the green body were produced in the same manner as in example 7, except that the above-described alumina powder was used as raw material.

The density of the sintered body was found to be 3.800 g/cm³. There was observed an infinite number of pores each with a size of more than 10 μm on the mirror-polished surface.

The pore occupied area after the corrosion test was found to be 2.3 %.

The above-described examples and comparative examples reveal as follows:

(1) When a prescribed alumina particle is used as raw material, a high density and high purity alumina sintered body with extremely less pores can be produced by a dispersion method without using a grinding medium.

(2) When alumina particles other than the ones prescribed in the present invention are used as raw material, a high density and high purity alumina sintered body with

extremely less pores cannot be produced by a dispersion method without using a grinding medium. Even if the molding pressure and sintering temperature are increased, the desired alumina sintered body cannot be produced (Comparative Examples 1, 2, 4, 7, and 8).

(3) When alumina particles other than the ones prescribed in the present invention are used as raw material, a high density and high purity alumina sintered body with extremely less pores cannot be produced even by a dispersion method using a grinding medium. (Comparative Examples 3).

(4) Even with alumina particles of the shape prescribed in the present invention, a high density alumina sintered body with extremely less pores cannot be produced in the case (Comparative Example 5) where the particle size is large, and the case (Comparative Example 6) where the particle size distribution is wide, and a large number of coarse particles are contained.

The present invention can provide an alumina sintered body which contains an extremely low amount of impurities and pores, and hence is suitable for the following items: that is, members to be in contact with a corrosive solution, gas, or the like, requiring corrosion resistance, such as products required to avoid mixing of other metallic elements, and adhesion or adsorption of dust particles, or the like, in the

semiconductor industry (ex., materials for the products such as vacuum chuck, vacuum pincette, and hands for use in operations including cleaning, transferring, and surface processing of a silicon wafer, and further a polishing instrument for magnetic materials); or materials for the products required to avoid the presence of pores itself, (ex., materials for a substrate for a hard disk, and a substrate for a magnetic head, materials for various kinds of industrial mirrors, and a dummy wafer). Further, there can be provided products with high reliability in strength and wear resistance as bioceramic members, and various kinds of structural components owing to the low amount of pores, i.e., defects. Still further, there can be provided decorative members such as plates and cups excellent in surface smoothness owing to no scattering of light due to pores.

What is claimed is:

1. A process for producing a polycrystalline alumina sintered body which comprises the steps of:

subjecting alumina powder to ultrasonic irradiation, mechanical stirring not using a grinding medium, or ultrasonic irradiation and mechanical stirring not using a grinding medium, resulting in slurry dispersed in a solvent; drying and forming said slurry to produce a green body; and then

sintering said green body in an air atmosphere at a temperature in the range of 1400 °C to 1800 °C;

wherein said alumina powder having a purity of 99.99 wt% or more comprises a polyhedral particle having substantially no fractured surface, and comprises α alumina particles having polyhedral shape; a D/H ratio of from 0.5 or more to 3.0 or less, wherein D represents a maximum particle diameter parallel to the hexagonal lattice plane of a hexagonal close packed lattice of α alumina, and H represents a maximum particle diameter perpendicular to the hexagonal lattice plane of a hexagonal close packed lattice of α alumina; the number-average particle size of from 0.1 μm or more to 1.0 μm or less; a D90/D10 ratio of 7 or less, wherein D10 and D90 are the particle sizes at 10 % cumulation diameter and 90 % cumulation diameter, respectively, from the smallest particle side in a cumulative particle size distribution.

2. The process according to claim 1, wherein an alumina powder added a sintering agent is subjected to ultrasonic irradiation, mechanical stirring not using a grinding medium, or ultrasonic irradiation and mechanical stirring not using a grinding medium, resulting in a slurry dispersed in a solvent.

3. The process according to claim 1, wherein the maximum diameter of pores in said polycrystalline alumina sintered body is $10\mu\text{m}$ or less, the number of said pores of from $1\mu\text{m}$ or more to $10\mu\text{m}$ or less per one mm^2 is 20 or less, said alumina purity is 99.99 % or more, and the density of said sintered body is 3.970 g/cm^3 or more.

4. The process according to claim 2, wherein the maximum diameter of pores in said polycrystalline alumina sintered body is $10\mu\text{m}$ or less, the number of said pores of from $1\mu\text{m}$ or more to $10\mu\text{m}$ or less per one mm^2 is 10 or less, said alumina purity is 99.99 % or more, and the density of said sintered body is 3.975 g/cm^3 or more.

5. The process according to claim 2, wherein said sintering agent is added to said alumina powder in an amount of from 10 ppm or more to 2000 ppm or less in terms of oxide.

6. The process according to claim 2, wherein said sintering agent is added to said alumina powder in an amount of from 10 ppm or more to 70 ppm or less in terms of oxide.

7. The process according to claim 2, wherein said

sintering agent is at least one compound selected from the group consisting of alkaline earth metal compounds and silicon compounds.

8. The process according to claim 2, wherein said sintering agent is a magnesium compound.

9. A semiconductor manufacturing equipment member obtained from said alumina sintered body according to claim 1.

10. Bioceramics obtained from said alumina sintered body according to claim 1.

11. A semiconductor manufacturing equipment member obtained from said alumina sintered body according to claim 2.

12 Bioceramics obtained from said alumina sintered body according to claim 2.

ABSTRACT

A process for producing a polycrystalline alumina sintered body which comprises the steps of:

subjecting alumina powder to ultrasonic irradiation, mechanical stirring not using a grinding medium, or ultrasonic irradiation and mechanical stirring not using a grinding medium, resulting in slurry dispersed in a solvent;

drying and forming said slurry to produce a green body; and then

sintering said green body in an air atmosphere at a temperature in the range of 1400 °C to 1800 °C;

wherein said alumina powder having a purity of 99.99 wt% or more comprises a polyhedral particle having substantially no fractured surface, and comprises α alumina particles having polyhedral shape; a D/H ratio of from 0.5 or more to 3.0 or less; the number-average particle size of from 0.1 μ m or more to 1.0 μ m or less; a D90/D10 ratio of 7 or less.

Table 1

	Alumina	Purity %	Primary particle μm	D90/D10	Shape	D/H	>10 μm ppm	Sintering agent	Amount added ppm
Example 1	AA04	99.99	0.40	4.8	Polyhedron	1	5		
Example 2	AA04	99.99	0.40	4.8	Polyhedron	1	5		
Example 3	AA02	99.99	0.20	6.0	Polyhedron	1	15		
Example 4	AA03	99.99	0.30	5.0	Polyhedron	1	10		
Example 5	AA07	99.99	0.70	3.6	Polyhedron	1	4		
Example 6	AA03	99.99	0.30	5.0	Polyhedron	1	10	Magnesium nitrate	200
Example 7	AA04	99.99	0.40	4.8	Polyhedron	1	5	Magnesium nitrate	500
Example 8	AA02	99.99	0.20	6.0	Polyhedron	1	5	Magnesium nitrate	50
Example 9	AA04	99.99	0.40	4.8	Polyhedron	1	5	Magnesia	500
Example 10	AA04	99.99	0.40	4.8	Polyhedron	1	5	Magnesium nitrate	1000
Example 11	AA05	99.99	0.50	4.5	Polyhedron	1	3	Magnesia	500
Example 12	AA07	99.99	0.70	3.6	Polyhedron	1	4	Magnesium nitrate	100
Example 13	AA04	99.99	0.40	4.8	Polyhedron	1	5	Magnesium nitrate	50
Example 14	AA04	99.99	0.40	4.8	Polyhedron	1	5	Magnesium nitrate	25
Comparative example 1	UA5055	99.99	0.30	5.8	Nonuniform	2	120		
Comparative example 2	UA5055	99.99	0.30	5.8	Nonuniform	2	120		
Comparative example 3	UA5055	99.99	0.30	5.8	Nonuniform	2	120		
Comparative example 4	UA5055	99.99	0.30	5.8	Nonuniform	2	120	Magnesium nitrate	500
Comparative example 5	AA2	99.99	2.00	3.0	Polyhedron	1	50	Magnesium nitrate	500
Comparative example 6	AA04	99.99	0.40	10.0	Polyhedron	1	209	Magnesium nitrate	500
Comparative example 7	Bayser	99.50	0.60	6.6	Nonuniform	3	790	Magnesium nitrate	500
Comparative example 8	Fine particle alumina	99.99	0.05	3.0	Nonuniform	5	Filtering impossible	Magnesium nitrate	500

036148-02799

	Molding method	Sintering temperature	Density of sintered body	Purity of sintered body	Number of pores $\leq 10 \mu m$	Number of pores $\geq 10 \mu m$	Corrosion test	Pore area prior to corrosion %	Pore area subsequent to corrosion %
Example 1	Press molding	1650	3.974	99.99	12	0	○	≤ 0.01	0.02
Example 2	Slip press molding	1650	3.977	99.99	18	0	○	≤ 0.01	0.02
Example 3	Press molding	1550	3.975	99.99	15	0	○	≤ 0.01	0.02
Example 4	Press molding	1600	3.980	99.99	5	0	○	≤ 0.01	0.01
Example 5	Press molding	1750	3.871	99.99	15	0	○	≤ 0.01	0.02
Example 6	Press molding	1550	3.984	99.98	7	0	○	≤ 0.01	0.02
Example 7	Press molding	1600	3.982	99.95	4	0	○	≤ 0.01	0.01
Example 8	Press molding	1600	3.982	99.99	5	0	○	≤ 0.01	0.01
Example 9	Slip press molding	1600	3.983	99.95	4	0	○	≤ 0.01	0.02
Example 10	Press molding	1600	3.980	99.90	5	0	○	≤ 0.01	0.01
Example 11	Tape molding	1550	3.982	99.95	6	0	○	≤ 0.01	0.02
Example 12	Press molding	1700	3.980	99.99	6	0	○	≤ 0.01	0.01
Example 13	Press molding	1600	3.981	99.99	7	0	○	≤ 0.01	0.01
Example 14	Press molding	1600	3.982	99.99	4	0	○	≤ 0.01	0.01
Comparative example 1	Slip press molding	1600	3.995	99.99	Large number	65	×	0.08	0.5
Comparative example 2	Press molding	1650	3.945	99.99	Large number	50	×	0.11	0.7
Comparative example 3	Press molding	1750	3.950	99.99	Large number	35	×	0.15	0.9
Comparative example 4	Press molding	1550	3.972	99.95	Large number	34	×	0.08	0.5
Comparative example 5	Press molding	1700	3.900	99.95	Large number	46	×	0.11	0.7
Comparative example 6	Press molding	1600	3.900	99.95	Large number	69	×	0.15	0.9
Comparative example 7	Press molding	1600	3.870	99.50	Large number	Large number	×	0.17	2.1
Comparative example 8	Press molding	1500	3.800	99.95	Large number	Large number	×	0.2	2.3

09364448.072799